# AINO MICRO Range VRLA






# SEALED RECHARGEABLE LEAD ACID BATTERY

Performance Spec	ifications						
Normal Voltage Number of cell	12V 6						
Normal Capacity	20 hour rate (250 mA to 10.5 volts): 5.00 Ah 10 hour rate (470 mA to 10.5 volts): 4.70 Ah 5 hour rate (900 mA to 10.2 volts): 4.50 Ah 1 hour rate (3.80 A to 9.00 volts): 3.80 Ah						
Internal Resistance	40 milliohms						
Weight	1.52 kg (3.63 lbs)						
Applicable Operating Temperature Range	-40°C(-40°F) to +70°C (+158°F)						
Ideal Operating Temperature Range	+20°C (+68°F) to +28°C (+82.4°F)						
Charge Retention (Shelf Life) at 68°F(20°C)	3 month	7% 1% 5%					
Standby Service	8 years						
Cycle Service	100% depth of discharge 50% depth of discharge 30% depth of discharge	350 cycles 650 cycles 1300 cycles					
Standard Terminals	Faston Tab No.187						
Intertek UL 1989		IEC.					

HIGH PERFORMANCE

- 5~8 years design life @ 25°C(77°F) ambient temperature;
- High quality and stability, using best 99.994% virgin pure lead;
- Rechargeable VRLA batteries with an electrolyte retained in a glass mat with a very fine glass fiber structure;
- Ultra-low water loss rates due to high compression absorption glass mat technology (AGM) with a reconstitution efficiency of over 99%;
- Proprietary Fixed Orifice Plate Pasting technology applying active materials on both sides of the grid for consistent cell-tocell performance, higher capacity and uniform grid protection;
- Perfect combination between energy storage performance and reliability;
- Up to 12 months shelf life due to low self-discharge rate (less than 3%/month at 25°C):
- Plate grid consisting of the high performance Lead Calcium Tin alloy for optimized corrosion resistance and long life;
- High impact resistant ABS resin cases and covers; ٠
- Available in UL94V-0 Flame Retardant Material;
- In compliance with IEC 60896-21/22, UL1989; ٠
- Wide operating temperature range.

## **Dimensions and Terminal**



Length : 90mm Width : 70mm Height : 94mm Total Height : 100mm





### Headquarter:

#### Shenzhen EverExceed Industrial Co., Ltd

- S Floor 19, Kechuang Building Hengchangrong High TechPark, Dezheng Road, Shiyan Bao'an District, Shenzhen.
- www.everexceed.com
- marketing@everexceed.com

### Branch Company:

**EverExceed International Company Limited (HK)** 


(2) 19H Maxgrand Plaza No3 Tai Yau St San PO Kong KLN Hongkong (info@everexceed.com

### EverExceed Corporation Ltd. (UK)

(2) Unit G25 WaterFront Studios, 1 Dock Road, London, United Kingdom Burope@everexceed.com


# **Innovative Features**






## **Performance Curves**








### **Discharge Characteristics**

Constant Current Discharge Characteristics - Amperes @ 25°C (77°F)												
Final VPC	5min	10min	15min	20min	25min	30min	45min	60min	90min	120min	180min	240min
1.80	17.4	12.2	8.87	7.18	6.41	5.50	4.01	3.22	2.33	1.88	1.30	1.04
1.75	19.3	13.3	9.50	7.60	6.63	5.64	4.13	3.28	2.39	1.91	1.32	1.07
1.67	21.9	14.7	10.1	7.90	6.83	5.81	4.53	3.34	2.43	1.93	1.32	1.08

Constant Current Discharge Characteristics - Watts Per Cell @ 25°C (77°F)												
Final VPC	5min	10min	15min	20min	25min	30min	45min	60min	90min	120min	180min	240min
1.80	29.4	20.6	14.6	11.8	10.5	9.03	6.59	5.41	3.96	3.21	2.24	1.82
1.75	32.7	21.8	15.5	12.4	10.8	9.19	6.73	5.49	4.04	3.25	2.27	1.84
1.67	37.0	23.6	17.0	13.4	11.5	9.82	7.13	5.70	4.18	3.34	2.31	1.87




Ð











www.exerexceed.com

Q

0

### Headquarter:

### Shenzhen EverExceed Industrial Co., Ltd

⑦ Floor 19, Kechuang Building Hengchangrong High TechPark, Dezheng Road, Shiyan Bao'an District, Shenzhen.

www.everexceed.com

marketing@everexceed.com

### Branch Company:

EverExceed International Company Limited (HK)

⑨ 19H Maxgrand Plaza No3 Tai Yau St San PO Kong KLN Hongkong ு info@everexceed.com

### EverExceed Corporation Ltd. ( UK )

(2) Unit G25 WaterFront Studios, 1 Dock Road, London, United Kingdom (3) Europe@everexceed.com